

Specification Approval Sheet(Cell)**产品规格确认书（电芯）**

受控 07

Model: NaCP50160118-70E3型号: NaCP50160118-70E3

Compiled By	Proofreaded By	Audited By	Approved By
马玉兵	李丹丹	滕磊	李金明

Customer Approval	Signature	Date
	Company Name:	
	Company Stamp:	

Content**目录**

1. Scope 适用范围	P04
2. Model 型号	P04
3. Specification 产品规格	P04
4. Battery Cell Performance Criteria and Test Conditions 电芯性能标准以及测试条件	P05
4.1 Standard environmental test condition 测试环境条件	P05
4.2 Electrical characteristics 电气特性	P05
4.3 Safety Performance 安全性能	P08
4.4 Visual inspection 外观检测	P09
5. Storage and Others 存储性能及其他	P09
6. Battery Cell Drawing 电芯尺寸图	P10
7. Appendix 附件	P10
8. Limited Warranty and Liabilities 有限保证和责任	P12
9. Appendix 附件	P13
Handling Precautions and Guideline For Li-ion Rechargeable Batteries	
钠离子充电电芯操作指示及注意事项	
1. Charging 充电	
2. Discharging 放电	
3. Notice for Designing of Battery Pack Structure 电池结构设计注意事项	
4. Storage 存储	
5. User's Guideline for Safety Handling: 用户安全操作信息	
6. Others 其它事项	
Customer Inquiry 客户调查	P18

1 Scope

This document describes the Product Specification of the Sodium-ion rechargeable battery cell supplied by JiangSu Highstar Battery Manufacturing Co.,LTD.

适用范围

本规格说明书描述了江苏海四达电源有限公司生产的可充电钠离子电芯的产品性能指标。

2 Model: NaCP50160118-70E3

型号: NaCP50160118-70E3

3 Specification**规格**

No.	Items (项目)	Specifications (规格)
3.1	Charge voltage 充电电压	3.95V
3.2	Nominal voltage 标称电压	3.05V
3.3	Nominal capacity 标称容量	70Ah
3.4	Standard Charging Current 标准充电电流	0.5C
3.5	Max. charge current 允许最大充电电流	1C
3.6	Discharge cut-off voltage 放电截止电压	1.8V
3.7	Standard Discharging Current 标准放电电流	0.5C
3.8	Max. Discharge current 允许最大放电电流	Under the conditions of 25°C ±2°C, Discharging at 3C for 30s at 100% SOC 在25°C ±2°C条件下, 100%SOC状态下, 3C放电30秒
3.9	Operating temperature Relative humidity % 工作温度、湿度	Charging : -20°C-55°C, 65% ±20%RH 充电: -20°C-55°C, 65% ±20%RH
		discharging : -40°C-60°C, 65% ±20%RH 放电: -40°C-60°C, 65% ±20%RH
3.10	Recommended Storage temperature 推荐存储温度	15°C-35°C
3.11	Cell Weight 电芯重量	1.8±0.2kg
3.12	Impedance 内阻	≤0.5mΩ
3.13	Cell dimension 电芯尺寸	厚度 thick : 50.1±1.0mm (200kgf, SOC Delivery) 宽度 Width : 160±0.8mm

4 Battery Cell Performance Criteria and Test Conditions**电芯性能标准以及测试条件****4.1 Standard environmental test conditions****标准测试环境**

Unless otherwise specified, all tests in this standard are carried out under the test conditions required by the test items: tests beyond this condition will produce obvious deviation to the test results.

Temperature : 25 °C ±2 °C

Relative Humidity : 65% ±20%

Under 200kgf ±20kgf preload

除非特别说明，本标准中所有测试均在测试项目要求的测试条件环境下进行：超出此条件环境下的测试均会对测试结果产生明显偏差。

温度：25 °C ±2 °C

湿度：65% ±20%

初始夹紧力：200kgf ±20kgf

4.2 Electrical characteristics**电气性能**

No.	Items (项目)	Test Method and Condition (测试方法和条件)	Criteria (标准)
4.2.1	Standard Charge condition 标准充电	Charging the cell with constant current at 0.5C and then with constant voltage at 3.95V till charge current declines to $\leq 0.05C$. 0.5C恒流充电至3.95V，再恒压3.95V充电直至充电电流 $\leq 0.05C$ 。	Charge Voltage = 3.95V 充电电压 = 3.95V Charge Rate = 0.5C 充电倍率 = 0.5C
4.2.2	Rapid Charge condition 快速充电	Charging the cell initially with constant current at 1C and then with constant voltage at 3.95V till charge current declines to $\leq 0.05C$. 1C恒流充电至3.95V，再恒压3.95V充电直至充电电流 $\leq 0.05C$ 。	Charge Voltage = 3.95V 充电电压 = 3.95V Charge Rate = 1C 充电倍率 = 1C
4.2.3	Standard Discharge condition 标准放电	The capacity means the discharge capacity of the cell, which is measured with discharge current of 0.5C with 1.8V cut-off voltage after standard charge. 该容量是指标准充电后，0.5C放电至1.8V。	Discharge Voltage = 1.8V 放电电压 = 1.8V Discharge Rate = 0.5C 放电倍率 = 0.5C
4.2.4	Initial Impedance 初始内阻	Internal resistance measured at AC 1KHz within 1 hour after standard charge 将电池按标准充电方法充电后，在1小时内测量其AC 1KHz下的交流阻抗。	$\leq 0.5m\Omega$
4.2.5	Cell Voltage 电池电压	Cell state upon shipment 出货状态	2.5-3.0V

No.	Items (项目)	Test Method and Condition (测试方法和条件)	Criteria (标准)
4.2.6	Initial Capacity 初始容量	<p>(1)Prior to charging, the cell shall be discharged at a constant current of 0.5C down to the cutoff discharge voltage 1.8V, rest for 10 minutes. 充电前, 电池以0.5C的恒流放电至截止电压1.8V, 休息10分钟.</p> <p>(2)The capacity means the discharge capacity of the cell, which is measured with discharge current of 0.2C with 1.8V cut-off voltage after standard charge. 该容量是指标准充电后, 0.2C放电至1.8V的容量</p> <p>(3)If the discharge capacity fails to meet the standard requirements, this test is allowed to be repeated 3 times 如果放电容量达不到标准要求,此项测试允许重复3次.</p>	<p>0.2C Capacity \geq 70Ah 0.2C容量 \geq 70Ah</p>
4.2.7	Rate capability 倍率性能	<p>(1) Prior to charging,the cell shall be discharged at a constant current of 0.5C down to cutoff discharge voltage 1.8V,rest for 10 minutes. 充电前, 电池应以0.5C的恒流放电至截止电压1.8V, 休息10分钟.</p> <p>(2)0.5C CC to 3.95V,and CV to 0.05C cut off, rest for 10 minutes. 0.5C恒流充电至3.95V, 再3.95V恒压充电至电流小于0.05C, 搁置10分钟.</p> <p>(3) The capacity means the discharge capacity of the cell, which is measured with discharge current of 1C with 1.8V cut-off voltage. 以1C放电至1.8V.</p>	<p>\geq96% Nominal capacity \geq96% 标称容量</p>
4.2.8	Low Temperature Performance 低温性能	<p>(1)The cell shall be charged in accordance with the standard charge.</p> <p>(2) The cell shall be stored in the temperature of $-20^{\circ}\text{C} \pm 2^{\circ}\text{C}$ for 4h.</p> <p>(3)Discharge at the constant current of 1C down to the end-of-discharge voltage 1.8V. 按标准充电方法充电后, 放入$-20^{\circ}\text{C} \pm 2^{\circ}\text{C}$低温箱中恒温4h, 在此条件下1C放电至1.8V。</p>	<p>discharge capacity \geq 80% Nominal capacity 放电容量 \geq 80% 标称容量</p>
4.2.9	High Temperature Performance 高温性能	<p>(1)The cell shall be charged in accordance with the standard charge.</p> <p>(2) The cell shall be stored in the temperature of $55^{\circ}\text{C} \pm 2^{\circ}\text{C}$ for 4h.</p> <p>(3)Discharge at the constant current of 1C down to the end-of-discharge voltage 1.8V. 按标准充电方法充电后, 放入$55^{\circ}\text{C} \pm 2^{\circ}\text{C}$高温箱中恒温4h, 在此条件下1C放电至1.8V。</p>	<p>discharge capacity \geq 96% Nominal capacity 放电容量 \geq 96% 标称容量</p>

No.	Items (项目)	Test Method and Condition (测试方法和条件)	Criteria (标准)
4.2.10	Charge Retention and Recovery at Room Temperature 常温荷电保持与容量恢复能力	After the cell is fully charged according to the standard method, it is stored at 25 °C ± 2 °C for 30 days, and then discharged at 0.5C at 25 °C ± 2 °C until the discharge termination voltage is 1.8V. This discharge capacity is maintained by charge. After the cell is recharged, the cell is discharged at a current of 0.5C at 25 °C ± 2 °C until the discharge termination voltage is 1.8V. This discharge capacity is restored by the charge. 电池按标准方法充满电后, 在25°C ± 2°C下储存30天后, 在25°C ± 2°C下以0.5C电流放电, 直到放电终止电压1.8V, 此放电容量为荷电保持。电池再充电后在25°C ± 2°C下以0.5C电流放电, 直到放电终止电压1.8V, 此放电容量为荷电恢复。	Capacity Retention ≥ 90% Nominal capacity 荷电保持 ≥ 90% 标称容量 Capacity Recovery ≥ 95% Nominal capacity 荷电恢复 ≥ 95% 标称容量
4.2.11	Standard Cycle Life 标准循环寿命	Temperature : 25 °C ± 2 °C Relative Humidity : 65% ± 20% under 200kgf ± 20kgf preload Charge: Charging the cell with constant current at 0.5C and then with constant voltage at 3.9V till charge current declines to ≤ 0.05C, rest for 30mins. Discharge: 0.5C discharge to 2.0V, one cycle is finished, then rest for 30mins. Then repeat above steps, when capacity is less than 80% of initial capacity, the cell life is over. 温度: 25 °C ± 2 °C 湿度: 65% ± 20% 初始夹紧力: 200kgf ± 20kgf 充电: 0.5C 恒流恒压充电至 3.9V, 截止电流 0.05C, 充完后搁置 30分钟 放电: 0.5C 放电到 2.0V, 完成一个循环, 搁置 30分钟。重复上述步骤。当放电容量小于 80% 初始容量, 寿命终止	≥ 2000 cycles

4.3 Safety Performance

安全性能测试

No.	Items (项目)	Test Method and Condition (测试方法和条件)	Criteria (标准)
4.3.1	Overdischarge 过放	After standard charge, the cell shall be discharged at constant current of 1C, discharging time: 90mins, Observe 1h. 电池标准充电后, 以1C电流放电90分钟, 观察1小时。	No Leakage, No Explosion or Catch Fire 不爆炸、不超火、不漏液
4.3.2	Overcharge 过充	After standard discharge, the cell shall be charged at 1C with cutoff voltage 5V or charging time reached 90min, Observe 1h (one of the conditions is preferred to stop test). 电池标准放电后, 以1C电流充电, 至蓄电池电压达到5V或充电时间达到90分钟, 观察1小时 (其中一个条件优先达到即停止试验)。	No Fire, No Explosion 不爆炸、不超火

No.	Items (项目)	Test Method and Condition (测试方法和条件)	Criteria (标准)
4.3.3	Short Test 短路试验	After standard charge, the external short circuit for 10 min, the external circuit resistance $\leq 5m\Omega$, Observe 1h. 电池充电后, 经外部短路10分钟, 外部线路电阻应小于 $5m\Omega$, 观察1小时。	No Fire, No Explosion 不爆炸、不起火
4.3.4	Fall Test 跌落试验	After standard charge, cell's positive and negative terminals fall down from 1.5m height to the concrete ground, Observe 1h. 电池充电后, 电池正负极端子向下从1.5m高度处自由跌落到水泥地上, 观察1小时。	No Fire, No Explosion 不爆炸、不起火
4.3.5	Heating Test 加热试验	After standard charge, the cell shall be stored in a oven with the heat rate of $5^{\circ}C/min \pm 2^{\circ}C/min$ up to $130^{\circ}C \pm 2^{\circ}C$, maintain 30mins, Observe 1h. 电池充电后放入烘箱, 烘箱按照 $5^{\circ}C/分钟 \pm 2^{\circ}C/分钟$ 的速率由室温升至 $130^{\circ}C \pm 2^{\circ}C$, 保持此温度30分钟后停止加热。观察1小时。	No Leakage, No Explosion or Catch Fire 不爆炸、不起火、不漏液
4.3.6	Crush Test 挤压试验	After standard charge, according to the following test conditions: 1) crush direction: perpendicularly to the cell plates, 2) crush plate shape: half cylinder of radius 75mm, the length of the half cylinder is larger than the size of the cell, 3) crush speed: (5 ± 1) mm/s, 4) crush degree: until the cell voltage is 0 V or deformation reaches 30% or crush force reaches 200kN, 5) Observe 1h. 电池充电后, 按下列条件进行试验: 1) 挤压方向: 垂直于蓄电池极板方向, 2) 挤压板形式: 半径75mm的半圆柱体, 半圆柱体的长度L大于被挤压电池的尺寸, 3) 挤压速度: (5 ± 1) mm/s, 4) 挤压程度: 电压达到0V或变形量达到30%或挤压力达到200kN后停止挤压, 5) 观察1小时。	No Fire, No Explosion 不爆炸、不起火
4.3.7	Low Pressure Test 低气压	The cells are to be stored for 6 hours at an absolute pressure of 11.6 kPa. 满电态电池放置于真空箱室, 抽真空至11.6kPa保持6小时。	No Leakage, No Fire, No Explosion 不泄露、不起火、不爆炸
4.3.8	Seawater Immersion Test 海水浸泡试验	After standard charge, cell soaks in salt water (3.5wt% NaCl aqueous solution), total immersion, the experiment lasts for 2h. 电池标准方法充电, 将电池在盐水中 (3.5%质量浓度NaCl水溶液) 浸泡, 盐水应将电池全部浸没, 实验持续2h。	No Fire, No Explosion 不爆炸、不起火

No.	Items (项目)	Test Method and Condition (测试方法和条件)				Criteria (标准)
4.3.9	Temperature Cyclic Test 温度冲击试验	After standard charge, the cell is put into the oven, cycling according to following chart, cycle 5 times, observe 1h. 电池标准方法充电, 电池放入温度箱中, 按照下图表进行调节, 循环次数5次, 观察1小时。				No Leakage, No Fire, No Explosion 不泄露、不起火、不爆炸
		温度 (°C)	时间增量 (分钟)	累计时间 (分钟)	温度变化率 (°C/分钟)	
		25	0	0	0	
		-40	60	60	13/12	
		-40	90	150	0	
		25	60	210	13/12	
		85	90	300	2/3	
		85	110	410	0	
		25	70	480	6/7	

4.4 Appearance inspection 外观检测


There shall be no such defect as scratch, flaw, crack, and leakage, which may adversely affect commercial value of the cell.

不允许有任何影响电芯性能的外观缺陷, 诸如裂纹、裂缝、泄漏等。

5 Cell drawing (all unit in mm, not in scale, included wrapped foil) 电芯尺寸图 (包胶)

正负极极柱为铝极柱 the positive terminal and negative terminal is aluminum

单位: mm



6.Special Warning 特别提示

Handling Precautions and Guideline for Sodium-Ion Rechargeable Batteries

钠离子充电电芯使用指示及注意事项

Statement (1):

Customers are requested to contact HIGHSTAR in advance, if and when the customer needs other applications or operating conditions than those described in this document. Additional experimentation may be required to verify performance and safety under such conditions.

声明一:

客户若需要将电芯用于超出文件规定以外的设备,或在文件规定以外的使用条件下使用电芯,应事先联系海四达,因为需要进行特定的实验测试以核实电芯在该使用条件下的性能及安全性。

Statement (2):

HIGHSTAR will take no responsibility for any accident when the cell is used under other conditions than those described in this Document.

声明二:

对于在超出文件规定以外的条件下使用电芯而造成的任何意外事故,海四达概不负责。

Statement (3):

HIGHSTAR will inform, in a written form, customers of improvement(s) regarding proper usage and handling of cells, if it is deemed necessary.

声明三:

如有必要,海四达会以书面形式告知客户有关正确操作使用电芯的改进措施。

Statement (4):

The cell must be used under the protection of power management system; When used in combination, the power management system must have the equalization function to balance the voltage difference in the battery pack and ensure the normal performance of the battery pack.

声明四:

电池使用时须在有电源管理系统保护下使用;组合使用时,电源管理系统必须具有均衡功能,能对电池组内电压差进行均

Statement (5):

During designation of host device or battery pack, it's better for customers to get HIGHSTAR involve to review the cell installation and safety protection scheme. This is very helpful to safety of cell application.

声明五:

客户在产品的设计过程中,最好邀请海四达共同完成电池安装及电池安全保护装置部分的设计,这对电池的安全使用会很有帮助。

6.1 Charge 充电**6.1.1 Charging current:**

Charge current should be less than the maximum value specified in the Product Specification. Charging with current higher than the recommended value may deteriorate the charge and discharge performance, mechanical performance and safety performance of the cell, and may lead to heating or leakage, which will seriously affect the service life of the cell. If you have special needs, please contact with the company.

充电电流:

充电电流不得超过本标准书中规定的最大充电电流。使用高于推荐值电流充电将可能引起电芯的充放电性能、机械性能和安全性能等变差,并可能会导致发热或泄漏,会严重影响电池使用寿命。如有特殊需要,请与公司联系沟通。

6.1.2 Charge Voltage limit:

Batteries shall be charged shall be done by voltage less than that specified in the Product Specification (3.95V/cell). Charging beyond 3.95V, which is the absolute maximum voltage, must be strictly prohibited. The charger and protection circuit of battery pack shall be designed to comply with this condition. It is very dangerous that charging with higher voltage than the maximum value and may cause damage to the cell electrical, mechanical safety performance and could lead to heat generation or leakage. In serious cases, it will affect the service life of the cell and even cause safety problems.

充电电压限制

充电电压不得超过本规格书中规定的额定电压（3.95V/电芯）。3.95V为充电电压最高极限，充电器和电池保护电路的设计应满足此条件。电芯电压高于额定电压值时，将可能引起电芯的充放电性能变差、可能会导致发热或泄漏，严重时会影响电池使用寿命甚至会产生安全问题。

6.1.3 Charge Temperature:

Batteries shall be charged at -20 °C-55 °C environment temperature specified in the Product Specification. In case of environment temperature is lower than 0 °C, batteries shall be charged with a little current (no larger than 0.2C).

充电温度:

电芯必须在-20 °C~55 °C 的环境温度范围内才能进行充电。环境温度低于0 °C时，须以小电流（不大于0.2C）充电；

6.1.4 Prohibition of Reverse Charge:

Reverse charging is prohibited. Cells shall be connected correctly. The polarity has to be confirmed before wiring. In case of the cell is connected improperly, the cell cannot be charged. the reverse charging may cause damage to the cell which may lead to degradation of cell performance and damage the cell safety, and could cause heat generation or leakage.

禁止反向充电:

正确连接电池的正负极，严禁反向充电。若电池正负极接反，应保证无法对电芯进行充电。反向充电会降低电芯的充放电性能、安全性，并会导致发热、泄漏。

6.2 Discharge 放电**6.2.1 Discharge current:**

The cell shall be discharged at less than the maximum discharge current specified in the Product Specification. High discharging current may reduce the discharge capacity significantly or cause over-heat. At the same time, it will seriously affect the service life of the cell.

放电电流:

放电电流不得超过本规格书规定的最大放电电流，大电流放电会导致电芯容量剧减并导致过热，同时会严重影响电池使用寿命。

6.2.2 Discharge Temperature:

Cells shall be discharged at -40 °C~60 °C environment temperature specified in the Product Specification. The optimum discharge temperature range is 25 °C~ 35 °C; The discharge current shall be controlled when it exceeds the optimal temperature range, otherwise the service life will be affected. If necessary, please contact the company.

放电温度:

电芯可在 -40 °C~60 °C 的环境温度范围内进行放电，最佳放电温度范围25 °C~35 °C；超出最佳温度范围使用时需对放电电流进行控制，不然会影响使用寿命，如有需要，请与公司联系沟通。

6.2.3 Over-discharge:

It should be noted that cells would be at an over-discharged status due to self-discharge characteristics in case they were not used for a long time. In order to prevent over-discharging, cells shall be charged periodically to maintain the voltage between 1.8V and 3.0V. Over-discharging may cause the loss of cell performance, characteristics , or cell functions.

过放电:

需注意的是，在电芯长期停止使用期间，它可能会因其自放电特性而处于某种过放电状态。为防止过放电的发生，电芯应定期充电，将其电压维持在1.8V至3.0V之间。过放电会导致电芯性能、电池功能的丧失。

6.3 Other requirements for charging and discharging:

If many cells are used in the same group, try to make the cells charge and discharge under the same current and temperature. If there are differences, there will be differences in the performance of the same group of cells, which will affect the performance of the whole battery pack if in serious case.

充放电其余要求:

如是许多电芯同组使用，要尽量使电芯在相同的电流和温度等环境下进行充放电使用，如有差异会对同组电芯的性能产生差异，严重时会影响整组电池性能的发挥。

6.4 Notice for Designing Battery Pack 电池结构设计注意事项

6.4.1 Pack Design 外壳设计

Battery pack should have sufficient strength to make sure the cell(s) inside is protected from mechanical shock.

电池外壳应有足够的机械强度以保证其内部电芯免受机械损伤，材质为阻燃性材料。

6.4.2 Cell Fixing 电芯的安装

6.4.2.1 No cell movement in the battery pack should be allowed.

电芯不得在壳内活动。

6.4.2.2 Prevention of short circuit in a battery pack or host device.

防止电芯在电池包装或主机内产生短路。

6.4.2.3 Enough insulation layers between wiring and the cells shall be used to maintain extra safety protection. The battery pack or host device shall be structured with no any potential short circuit, which may cause generation of smoke or firing.

引线与电芯之间要有足够的绝缘层以保证绝对安全。电池壳内不得有任何短路发生隐患，以防止冒烟或着火。

6.5 Storage 贮存

The cell shall be stored at the environmental condition of -20 °C- 45 °C and 65% ±20% RH. Long term storage will cause irreversible damage to cell performance.

The voltage for a long time storage shall be 1.8V-3.0V range.

If the cell has to be storied for a long time (Over 3 months), the environmental condition should be:

Temperature: 15 °C-35 °C

Humidity: 65% ±20%RH

During the warranty period, the cell with cell voltage lower than 1.8V shall be recharged with 10A ~ 50A current every 3 months until the voltage reaches 3.0V, otherwise it will cause great irreversible damage to the cell performance.

电芯储存可在温度 -20 °C~ 45 °C，湿度为65% ±20%RH的环境中，长期储存会对电池性能产生不可逆损伤。

长期存储电池（超过3个月）须置于温度为15 °C-35 °C、湿度为65% ±20%RH的环境中，电压为1.8V~3.0V。

保质期内每隔3个月对电池电压低于1.8V的电池用10A~50A电流进行充电，至电压达到3.0V，不然会对电池性能产生较大不可逆损伤。

6.6. Application conditions 应用条件

Customer shall ensure that the following application conditions in connection with the products are strictly observed:

客户应当确保严格遵守以下与电池相关的应用条件。

6.6.1. Customer shall procure that each product shall be used under the strict monitor, control and protection by the BMS incorporated by HIGHSTAR. When the cell is first used, it must be fully charged and discharged for activating it and giving fully capacity.

客户应配置电池管理系统，严密监控、管理与保护每个电池。电芯初次使用必须进行小电流满充满放以激活，以保证后续使用中容量的充分发挥。

6.6.2 Customer shall keep relevant records of the BMS monitoring data throughout the entire service life of each product, including keeping record of number of occurrence of rush charge, which could be used in the determination and judgment of any product warranty and liability claim entitlement. No warranty or liability claim should be considered without BMS diagnosis records (at a regular basis, esp. during maintenance) of the relevant product.

客户应保存完整的电池运转的监测数据，用作产品质量责任划分的参考。不具备完整的电池系统使用期限内的监测数据的，海四达不承担产品质量保证责任。

6.6.3 Prevent draining any product down to over discharge state. A product may be permanently damaged internally when the cell voltage is lower than 1.8 V and which shall be strictly prohibited, failing what HIGHSTAR's warranties under the contract shall cease to apply, thereby releasing the HIGHSTAR from any liability in connection therewith. After discharge cut-off in accordance with paragraph 3.6, internal power consumption of the system should be reduced to a minimum to prolong the idle time before recharge. Customer undertakes to educate the users of the products or other parties who may come to handle the products to recharge the cells at minimum time intervals to prevent reaching the over-discharge state.

避免电池到达过放状态。电池电压低于1.8V时，电池内部可能会遭到永久性的损坏，此时海四达的产品质量保证责任失效。根据本技术协议第3.6条，当实际放电截止电压低于标准放电截止电压时，系统内部能耗降低到最小，并在重新充电之前延长休眠时间。客户需要培训使用者在最短的时间内重新充电，防止电池进入过放状态。

6.6.4 Batteries should avoid charging at low temperatures prohibited by this Technical Agreement (including standard charging, fast charging and emergency charging), otherwise accidental capacity reduction may occur. Battery management system should be controlled with different charging current according to different temperatures specified in this agreement. It is forbidden to charge under the temperature stipulated in this technical agreement. Otherwise, HIGHSTAR will not undertake the responsibility of quality assurance.

电池避免在本技术协议禁止的低温条件下充电(包括标准充电, 快充, 紧急情况充电), 否则可能出现意外的容量降低现象。电池管理系统应依照本协议规定的不同温度以不同的的充电电流进行控制。禁止在低于本技术协议规定的温度条件下充电, 否则海四达不承担质量保证责任。

6.6.5 The design of the electric box must fully consider the heat dissipation problem of the cell. HIGHSTAR does not take the responsibility due to the overheating of the cell or batteries caused by the thermal design problem of the electric box.

电箱设计中应充分考虑电芯的散热问题, 由于电箱散热设计问题导致的电芯或电池过热损坏, 海四达不承担质量保证责任

6.6.6 The design of the electric box must fully consider the waterproof and dustproof problems of the cells. The electric box must meet the waterproof and dustproof grade stipulated by the relevant national standards. The HIGHSTAR does not take the responsibility due to damage to the cell or batteries (such as corrosion, rust, etc.) caused by water and dust.

电箱设计中应充分考虑电芯的防水、防尘问题, 电箱必须满足UL和IEC有关标准规定的防水、防尘等级。由于防水、防尘问题而导致的电芯或电池的损坏(如腐蚀、生锈等), 海四达不承担质量保证责任。

6.6.7. It is forbidden to mix different P/N batteries in the same battery system, otherwise, HIGHSTAR will not be responsible for quality assurance.

禁止不同P/N料号电芯在同一电池系统中混用, 否则海四达不承担质量保证责任。

6.7 User's Guideline for Safety Handling: 用户安全操作信息:

6.7.1 The following information, or equivalent statements, shall be made available to the user through one or more of the following means, as appropriate: printed on the label for the cell, printed on the label for host device, printed in the owner's manual, or posted in a help file or Internet website:

下列信息或类似的申明必须通过一种或多种适当的途径让用户知晓, 可选择的途径包括: 电池标签、主机标签、用户手册、储存于帮助文档或互联网:

6.7.1.1 Do not disassemble or open, crush, bend or deform, puncture, or shred;

请勿拆解或打开、挤压、弯折、变形、刺穿、敲碎;

6.7.1.2 Do not modify or remanufacture, attempt to insert foreign objects into the cell;

请勿修改或改装, 不要试图将外物插入电池;

6.7.1.3 Do not immerse cells into water or other liquids, or expose to fire, explosion, or other hazard.

禁止将电池浸入或暴露在水或其它液体中, 远离火源、爆炸物和其他危险;

6.7.1.4 Do not expose them to any high temperature environment exceeding operation temperature as set out in paragraphs 3.9&3.10, otherwise it may cause fire. At all use time, cell temperature should not exceed 60 °C, shut down system by BMS when it occurs.

禁止将电池长时间暴露在超过本技术协议第3.9条和第3.10条规定的温度条件的高温环境中, 否则可能会导致火灾。在任何正常的充放电使用情况下, 电芯温度不能超过60 °C, 如果电芯温度超过60 °C, 电池管理系统需关闭电池, 停止电池运行。

6.7.1.5 Only use the cell for the system for which it was specified.

只能使用本系统规定的电池;

6.7.1.6 Only use the cell with a charging system that has been qualified with the system per standard. Use of an unqualified cell or charger may present a risk of fire, explosion, leakage, or other hazard.

只能使用通过标准认证具有充电管理系统的电池, 使用未经认证的电池或充电器可能存在起火、爆炸、或其它危险;

6.7.1.7 Do not short circuit a cell or allow metallic or conductive objects to contact the cell terminals, otherwise high current and temperature may cause body injury or fire hazards. Metallic cell terminals exposed from plastic packaging and ample safety precautions should be implemented to avoid short circuiting them during system integration or connections.

禁止电池正负极短路, 也不要让金属或其它导体接触电池接电端子; 否则强电流和高温可能导致人身伤害或者火灾。在电池系统组装和连接时, 应有足够的安全保护, 以避免短路。

6.7.1.8 Replace the cell only with another cell that has been qualified with the system per standard. Use of an unqualified cell may present a risk of fire, explosion, leakage, or other hazard.

更换电池时只能使用通过标准认证的电池, 使用未经认证的电池可能存在起火、爆炸或其它危险;

6.7.1.9 Don't keep a cell at rest for a long time (over 6 months). Safety accident may happen when recharging a cell which has a rest for a long time.

避免电池长时间放置不用（6个月以上），长期放置不用的电池重新充电时可能会发生安全问题。

6.7.1.10 Promptly dispose of used batteries in accordance with local regulations.

按当地法规迅速处理报废电池；

6.7.1.11 Cell usage by children should be supervised.

儿童使用电池应受到监督；

6.7.1.12 Avoid dropping the phone or cell. If the phone or cell is dropped, especially on a hard surface, and the user suspects damage, take it to a service center for inspection.

不要跌落主机或电池，如果主机或电池不慎跌落（尤其在硬表面上），用户怀疑电池损坏，则应找服务中心检查；

6.7.1.13 Improper cell use may result in a fire, explosion, or other hazard.

不正确使用电池可能发生燃烧、爆炸或其它危险。

6.7.1.14 Products should be securely fixed to solid platform, and power cables should be securely attached by fastener to avoid intermittent contact which may cause arcing and sparks.

客户应将电池安全地固定在固体平面上，并将电源线安全地束缚在合适的位置，以避免摩擦而引起电弧和火花。

6.7.1.15 Do not service cells and electrical connections within plastic package of cell. Improper electrical connection within a cell may cause overheating in service.

严禁用塑料封装电池或用塑料进行电气连接。不正确的电气连接方式可能会造成电池使用过程中发生过热现象。

6.7.1.16. When the electrolyte leaks, skin and eye contact with the electrolyte should be avoided. In case of contact, a large amount of clean water should be used to clean the contact area and seek help from the doctor. It is forbidden for any person or animal to swallow any part or substance contained in the cell.

当电解液泄露时，应避免皮肤和眼睛接触电解液。如有接触，应使用大量的清水清洗接触到的区域并向医生寻求帮助。禁止任何人或动物吞食电池的任何部件或电池所含物质。

6.7.1.17 Protect cells from mechanical shock, impact and pressure. Internal electrical circuit may short circuit to generate high temperature and fire hazards.

尽力保护电池，使其免受机械震动、碰撞及压力冲击，否则电池内部可能短路，产生高温和火灾。

6.7.1.18 When cells charging is terminated improperly for reasons such as exceeding allowable charging time, cut-off due to exceeding charging voltage or cut-off due to exceeding charging current, all these events are defined as "improper charge termination". Such event may indicate that there is current leaking within a cell system or some components have started to malfunction and subsequent charging of such cell system without finding and fixing root cause of problem may cause potential overheat or fire hazards. When such event occurs, the BMS should lock itself up to prevent subsequent charging and notice should be given to the user to return the vehicle to dealer for servicing. Subsequent charging should only be resumed after the system has been thoroughly checked by qualified technician who can identify and fix root cause attributed to the "improper charge termination".

电池充电过程中可能发生不适当的终止充电现象。如：超出允许的充电时间充电，充电电压过高而终止充电或充电电流过强而终止充电。上述现象被定义为“不适当的终止充电”。当发生以上现象时，可能意味着电池系统出现漏电或某些部件出现故障。在没有找到根本原因并彻底解决之前继续对该电池充电可能会引起电池过热或发生火灾。当发生以上现象时，电池管理系统应该通过自动锁定功能，禁止后续的充电，并提醒使用者将装载有该电池的交通工具退回到经销商处进行系统维护。该电池只有经过有认证资格的技术人员全面检查，确定根本原因并彻底解决、改善后方可恢复充电。

6.7.1.19 Cell fire or explosion may be caused by improper operation during abuse test. The test can only be carried out in a professional laboratory by professionals equipped with appropriate protective equipment. Otherwise, it may lead to serious personal injury and property loss.

在进行滥用测试实验时如操作不当可能会引起电池起火或者爆炸。该测试实验只能由配备适当的防护装备的专业人员在专业的实验室进行。否则，可能会导致严重的人身伤害和财产损失。

6.7.2 The following indications, notifications, and dialog/messages, at the system level, or an equivalent statement, may be displayed along with recommended actions as appropriate:

下列指示、通告、语句、信息或类似的申明应通过适当途径让用户知悉：

6.7.2.1 Abnormal cell temperature alert.

不正常的电池温度警示；

6.7.2.2 Abnormal host device and/or cell dc input voltage alert.

不正常的主机或电池的直流输入电压警示；

6.7.2.3 Abnormal current draw alert.

不正常的电流警示；

6.7.2.4 Cell communication fail/time-out alert.

电池通讯失败或超时警示；

6.7.2.5 Incompatible cell alert.

不相容电池警示；

6.7.2.6 Alert for other malfunctions that may lead to hazards.

可能导致危险的其它故障警示。

6.8 Product end of life management 产品寿命终止管理

6.8.1 This cell is designed to service with a finite life time. The customer shall develop and implement an active tracking system to monitor and record impedance of each Product in its entire service life. HIGHSTAR and its customer shall come into agreement about internal resistance and capacity measurement methods, HIGHSTAR and/or its customer shall stop using any of the products when its resistance exceeds 200% of its internal resistance or it capacity fading to 70% of typical capacity (70Ah) @25 °C. Failure to comply with this requirement shall render HIGHSTAR's warranties under the Contract inapplicable, thereby releasing HIGHSTAR from any liability in connection therewith.

电池的使用期限是有限的。客户应该建立有效的跟踪系统监测并记录每个使用期限内电池的内阻和容量。内阻以及容量的测量方法和计算方法需要客户和海四达共同讨论和双方同意。当使用中的电池的内阻超过这个电池最初内阻的200%或容量小于等于标称容量70%(25 °C)，应停止使用电池。违反该项要求，将免除海四达依据产品销售协议以及本技术协议所应承担的产品质量保证责任。

6.8.2 The cell life determination conditions can refer to paragraph 4.2.11 cycle life. The service conditions not specified in this specification will affect the cycle life.

电芯循环寿命应是指在4.2.11条件下的循环寿命。不在此规格书规定的使用条件下均会影响循环寿命。

6.9 Others: 其它事项:**6.9.1 Prohibition of Disassembly 严禁拆卸电芯**

6.9.1.1 Never disassemble cells. The disassembling may generate internal short circuit in the cell, which may cause firing or other problems.

在任何情况下不得拆卸电芯。拆卸电芯可能会导致内部短路，进而引起着火及其它问题。

6.9.1.2 Electrolyte is harmful. In case the electrolyte come into contact with the skin, or eyes, physicians shall flush the electrolyte immediately with fresh water and medical advice is to be sought.

电解液有害。万一有电解液泄漏而接触到皮肤、眼睛或身体其它部位，应立即用清水冲洗电解液并就医。

6.9.2 Never incinerate nor dispose the cells in fire. These may cause firing of the cells, which is very dangerous and is prohibited.

在任何情况下，不得燃烧电芯或将电芯投入火中，否则会引起电芯燃烧，这是非常危险的，应绝对禁止。

6.9.3 The cells shall never be soaked with liquids such as water, seawater, drinks such as soft drinks, juices, coffee or others

不得将电芯浸泡液体，如淡水、海水、饮料（果汁、咖啡等）。

6.9.4 The cell replacement shall be done only by either cells supplier or device supplier and never be done by the user

更换电芯应由电芯供应商或设备供应商完成，用户不得自行更换。

6.9.5 Prohibition of use of damaged cells

禁止使用已损坏的电芯

6.9.6 The cells might be damaged during shipping by shock. If any abnormal features of the cells are found such as deformation of the cell package, smelling of an electrolyte, an electrolyte leakage and others, the cells shall never be used any more. The Cells with a smell of the electrolyte or a leakage shall be placed away from fire to avoid firing.

电芯在运输过程中可能因撞击等原因而损坏，若发现电芯有任何异常特征，如外壳破损，闻到电解液气味，电解液泄漏等，该电芯不得使用。有电解液泄漏或闻到异常味道的电池应远离火源以避免着火。

7.Limited Warranty and Liabilities 有限保证和责任**7.1 Limited Warranty period 有限保证期限**

The cells shall comply with this specification within 12 months from the manufacture date as stipulated on cell marking ("Warranty Period"). In the Warranty Period, HIGHSTAR will replace cells which fail to conform to this specification at no cost to Customer.

自电芯标识显示的制造日期之日起12月内（“保证期限”），电芯应符合本规格书的规定。在此保证期限内，海四达免费为客户更换不符合本规格书规定的电芯。

7.2. Disclaimer 免责声明

Under the following conditions, HIGHSTAR will not take any responsibility incurred in any losses resulting from the use of cells:

在以下条件下，海四达对客户因使用电芯而引起的任何损失不承担赔偿责任：

7.2.1. If the product demand unit does not use the product according to the provisions of this specification, causing social impact and affecting the reputation of HIGHSTAR, HIGHSTAR will investigate the responsibility of the product demand unit. According to the degree of impact on HIGHSTAR, the product demander should provide compensation to HIGHSTAR.

如果由于产品需求单位不按本说明书中的规定进行使用，造成社会性影响，并对海四达的声誉造成影响的，海四达将会追究产品需求单位的责任。根据对海四达造成的影响程度，产品需求单位需向海四达提供赔偿。

7.2.2 The cells are misused, abused or are used in any manner deviated or in breach of conditions as set out in this specification and beyond the allowable conditions of this specification.

误用、滥用电芯或违反本规格书规定和超出本规格书的允许条件使用的电芯；

7.2.3 The cells are rendered to be nonconforming to this specification for reasons caused by parties other than HIGHSTAR or by circumstances beyond the control of HIGHSTAR.

非海四达原因导致的或海四达不能控制的原因导致的电芯不符合本规格书的规定。

Before ordering HIGHSTAR products, the buyer needs to confirm the latest status of the products in advance with HIGHSTAR.

海四达保留在没有预先通知的情况下改变和修正设计及产品规格确认书的权力；买方在订购海四达产品前，需与海四达提前确认产品的最新状态。

7.2.5 English specifications are for reference only. Please refer to the technical specifications of the Chinese version.

英文规格释义仅供参考，请以中文版技术规格要求为准。

7.3 Limited Warranty range 有限保证范围

Customer is recommended to follow this specification to use. Or customer can use an alternative operation method mutually agreed by customer and HIGHSTAR. Using an operation method neither according to the specification nor agreed by HIGHSTAR in written will cause the resulting change in product quality are not applicable to the warranty scope promised by HIGHSTAR.

推荐客户完全按照此产品规格书上所描述的要求进行操作，或采用经过客户与海四达双方确认的其他条件。如果客户采用的使用方法既没有按照本规格书的要求，也没有经海四达具有法定有效的书面同意，所导致产品质量变化不适用于海四达公司承诺的保质保证范围内。

8. Risk Warning 风险警告

8.1 Waring statement 警示声明

WARNING

CELL ARE POTENTIALLY DANGEROUS AND PROPER PRECAUTIONS MUST BE OBSERVED IN HANDLING AND MAINTENANCE.

RUNNING TESTS ON THE CELLS IMPROPERLY MAY RESULT IN SEVERE PERSONAL BODY INJURY OR PROPERTY DAMAGES.

WORK ON CELLS MUST BE PERFORMED ONLY WITH PROPER TOOLS AND PROTECTIVE EQUIPMENT MUST BE USED.

CELL MAINTENANCE MUST BE CARRIED OUT BY PERSONNEL KNOWLEDGEABLE OF CELLS AND TRAINED IN THE SAFETY PRECAUTIONS INVOLVED.

FAILURE TO OBSERVE THE ABOVE MAY CAUSE VARIOUS HAZARDS.

警告

电池存在潜在的危險，在操作和维护时必须采取适当的防护措施！

不正确地滥用测试实验，可能导致严重的人身伤害和财产损失！

必须使用正确的工具和防护装备操作电池。

电池的维护必须由具有电池专业知识并经过安全培训的人士执行。

不遵守上述警告可能造成多种灾难。



PRODUCT SPECIFICATION

DOC NO.: NaCP50160118-70E3
SHEET : 17 OF 17
ECN NO. : Q/KAGG1415-2023

8.2. Types of Hazards 危险类型:

Customer acknowledges the following potential hazards in connection with the usage and handling of the Products:

客户知悉在电池使用和操作过程中存在以下潜在的危险:

8.2.1 Working with cell can expose the handler to chemical, shock and/or arcing hazards. Although a person's body might react to contact with direct current voltage differently than from contact with alternate current voltage, Customer shall take a conservative position and consider the risk of shock or electrocution to be the same for both alternate current and direct current exposures greater than 50 V.

操作者在操作时可能会受到化学品、电击或者电弧的伤害。尽管人体对遭受直流电与交流电的反应不同，但是高于50V的直流电压与交流电对人体的伤害是同样严重的，因此客户必须在操作中采取保守的姿势以避免电流的伤害。

8.2.2 Cells expose its handler to chemical hazards associated with the electrolyte used in the cell.

存在来自电池中的电解液的化学风险。

8.2.3 When selecting work practices and personal protective equipment, customer and its employees should consider potential exposure to these hazards and therefore prevent accidental short-circuit that can result in electrical arcing, explosion, and/or "thermal runaway" of the cells.

在操作电池和选择个人防护装备时，客户及其雇员必须考虑到以上潜在的风险，防止发生意外短路，造成电弧、爆炸或热失控。

Customer Inquiry 产品规格需求

Model: NaCP50160118-70E3

The customer is requested to write down your information and contact HIGHSTAR in advance, if the customer needs applications or operating conditions other than those described in this document. HIGHSTAR could design and build such products according to your special request if it is attainable

我司也可以根据客户的特殊要求而设计、制造符合要求的电池产品，如果贵公司有本规格书描述之外的性能要求，请您写在下面并回签给我司：

	Special Request	Criteria
	要求	规格
1		
2		
3		
4		
5		
6		
7		
8		
9		
10		

Company Name: _____

Signature: _____

Date: _____